Ducting Ancillaries

Alongside our ventilation systems and ducting, we offer a range of ancillary items.

Rigid Duct Aluminium Duct Tape - 45m & 100m



| Code | Length |
|---------|--------|
| 50TP45 | 45m |
| 50TP100 | 100m |

Overview

A 30 Micron soft tempered bright aluminium foil. Coated with high tack pressure adhesive which has excellent UV light resistance on a white glassine liner.

This product is recommended where a moisture barrier and cold weather performance is required.

| Technical data | Typical values | |
|-------------------------|--|--|
| Adhesive colour: | Clear | |
| Adhesive type: | Acrylic UV Light resistance | |
| Tape thickness: | 0.060mms (without liner) | |
| Foil thickness: | 0.030mms | |
| Peel adhesion to steel: | 1000N/M | |
| Loop tack: | 800N/M | |
| Shear (static): | 87 Hours @ 1kg | |
| Fire protection: | Conforms to Class O BS476 part 7 & 6 1987 | |
| Minimum applic temp: | 0°C | |
| Service range: | -20°C to 120°C | |
| Shelf life: | 12 months (PSMA Conditions) | |
| | | |

PVC Duct Tape (non flame retardant) – 4.6m & 33m



| Code | Length |
|-------|--------|
| 123-4 | 4.6m |
| 123 | 33m |

Applications

- ▶ Jointing of polythene sheeting
- Barrier tape to prevent electrolytic reaction
- Sealing insulation panels
- Patching, sealing (boxes, drums, kegs) repair

| Technical data | Typical values |
|----------------------|--------------------|
| Total thickness: | 0.14 mm |
| Adhesive power: | 200N/m |
| Backing thickness: | - |
| Tensile strength: | 2KN/m |
| Elongation: | 200% |
| Temperature: | -20°C to 80°C |
| Dielectric strength: | 6KV |
| Colours: | Black, White, Grey |
| Shelf life: | 12 months |

Warranties

The above figures are average values and should not be regarded as maximum or minimum values for specification purpose.

The purchaser shall be responsible for determining the suitability of this purpose. Goods which prove to be defected through

faulty material or workmanship must be returned to us carriage paid. These will be replaced or credited. We shall not be liable for consequential damage incurred in the use of this material. All slitting and length tolerances are to British Standards, but other tolerances are available by request.