Non-Metallic Systems Xtraflex XF Type A



Technical Characteristics					
Conforms to	Low voltage directive				
Approvals and Standards	(€				
Degree of mechanical protection	High Impact	Resistance			
Degree of protection	IP65 - As sta	andard			
UV protection	High				
Fitting Characteristics	Straight fittin		ernal male the	read	
Application		into threade	d entries or k METRIC Thre		locknut to secure
Normal operating temperature range	Application	Min Temp	Max Temp		
	Static	- 5°C	+60°C		
	Dynamic	- 5°C	+60 °C		
For use with - Conduit Series	Standard we	eight Xtraflex	Type XF		
Fire performance (Fittings ONLY	Test	Standard	Perfo	rmance Rating	
	ISC	4589-2		24%	
	BS EN	60695-2-11		850°C	Self Extinguishing
		UL94		V2	Low Smoke & Halogen Free
Testing data	Click or See	page <u>3</u>			
Type of material	Polyamide (Nylon) 66 - Body				
Image			NA.		

The Company's policy is one of continuous improvement and reserves the right to change specifications at any time without prior notice.



Non-Metallic Systems Xtraflex XF Type A




Dimensional & Thread Data

			Nominal Dimensions (mm)			
Part No Black Body Metric Threads	Nominal Conduit A	Thread B	С	D	E	F
XF12/M16/D	12	M16x1.5	8.0	22.0	11.5	35.5
XF16/M16/D	16	M16x1.5	10.0	27.0	11.5	35.5
XF16/M20/D	16	M20x1.5	10.0	27.0	13.0	37.0
XF20/M20/D	20	M20x1.5	13.5	33.0	13.0	43.5
XF25/M25/D	25	M25x1.5	19.0	43.0	15.5	52.5
XF32/M32/D	32	M32x1.5	25.0	47.0	16.5	53.5
XF40/M40/D	40	M40x1.5	31.0	59.0	16.5	54.5
XF50/M50/D	50	M50x1.5	40.6	72.0	16.5	55.5

Metric	Standard thread conforming to EN60423 & BS3643				
Thread Size	Ext Thread Outside Diameter	Int Thread Inside Diameter	Pitch		
M12	12mm	10.9mm	1.5mm		
M16	16mm	14.4mm	1.5mm		
M20	20mm	18.4mm	1.5mm		
M25	25mm	23.4mm	1.5mm		
M32	32mm	30.4mm	1.5mm		
M40	40mm	38.4mm	1.5mm		
M50	50mm	48.4mm	1.5mm		
M63	63mm	61.4mm	1.5mm		





The Company's policy is one of continuous improvement and reserves the right to change specifications at any time without prior notice.



Non-Metallic Systems Xtraflex XF Type A



Thermal Properties

Test Type	Methods / Standards	Requirements	Value
Dynamic Applications		5000 Operations at MBR 2hrs	-5°C to +60°C
Static Short Term Temp		Temporary Use (3000hrs)	-5°C to +60°C
Static Long Term Temp		Permanent Use (30,000) Hours	-5°C to +60°C

Flammability

Test Type	Method / Standard	Requirement	Result	Unit
Glow Wire	BS EN 60695-2-11	Extinguish within 30s	850°C	°C
Flammability	IEC 61386-1-12	1Kw Burner Flame to Self Extinguish	Pass	Pass/Fail
Oxygen Index	ISO 4589-2		24.1	%

Chemical Resistance Chart

	Astm No.1	Diesel oil	Methyl Bromide	Sulphur Dioxide (Gas)
	Astm No.2	Diethylamine	MEK	Sulphuric Acid (10%)
Key:	Astm No.3	Ethanol	Nitric Acid (10%)	Sulphuric Acid (70%)
	Acetic Acid (10%)	Ether	Nitric Acid (70%)	Toluene
Suitable :	Acetone	Ethylamine	Oxalic Acid	Transformer Oil
	Aluminium Chloride	Ethylene Glycol	Ozone (Gas)	1,1,1-Trichloroethane
Limited Suitability:	Aniline	Ethyl Ethanoate	Paraffin oil	Trichloroethylene
	Benzaldehyde	Freon 32	Petrol	Turpentine
Unsuitable :	Benzene	Hydrochloric Acid (10%) Phenol	Vegetable Oil
	Carbon tetrachloride	Hydrochloric Acid (36%) Sea Water	Vinyl Acetate
Not Tested :	Chlorine water	Hydrogen Peroxide (35°	%) Silver Nitrate	Water
	Chloroform	Hydrogen Peroxide (87°	%) Skydrol	White Spirit
	Citric Acid	Lactic Acid	Sodium Chloride	Zinc Chloride
	Copper Sulphate	Lubricating oil	Sodium Hydroxide (10%	b)
	Cresol	Methanol	Sodium Hydroxide (60%	5)

The information above is given as a guide only and is based on published technical data and experience. The chemical resistance of the above products is dependant on factors such as chemical exposure, concentration of the chemical and temperature. The above chemicals are valid for a temperature of 23°C. Use of the above table is at the users own discretion and risk. Those using it must satisfy themselves that their application presents no health and safety risks. The end user should assess compatibility with their application and contact Thomas & Betts for further information.

ADHERENCE TO THE CURRENT WIRING REGULATIONS BS7671 OR NEC WIRING REGULATIONS (FOR USA) IS STRONGLY ADVISED.

MINIMUM BEND RADIUS FOR FLEXING IS DEPENDANT UPON MINIMUM TEMPERATURE, BENDING FREQUENCY AND CHEMICAL ENVIRONMENT.

The Company's policy is one of continuous improvement and reserves the right to change specifications at any time without prior notice.

